



Aluminum Rainware Accessories Specifications Sheet

MATERIALS

A. All ACM Rainware accessories shall be made of a 3105 / 3025 - type aluminum coil sheet H24, or equivalent, as referenced in Aluminum Standards and Data, Table 7.1. The metal shall be treated on both sides with a non-chromate chemical conversion coating to ensure proper paint adhesion and resistance to corrosion. ACM rainware products shall be coated on the front side with ACM's baked on, high performance, Polykote® 3000 paint system that is specifically formulated for residential exterior applications. The backside of all products shall be coated with a full coat of Polyester Backer finish unless specified otherwise. The nominal film thickness of Smooth coatings shall be a 0.70 mil on the front side and 0.20 mil on the backside.

B. Physical Properties of Coated Surface:

- a. Coated film hardness achieves F-2H pencil as tested per ASTM D3363
- b. Solvent Resistance: 50 ~ 100+ MEK rubs as tested per ASTM D4752
- c. Flexibility: Nominal 2-T180 NTO (subject to method of forming & metal thickness) as measured by ASTM D4145-83
- d. Reverse Impact: 1.5X metal thickness NTO ASTM D2794

Accelerated Weathering:

- a. 5% Salt Spray (1000 hours) no creep over 1/32" from scribe ASTM B 117
- b. 100% Humidity: No significant visual change after 1,000 HR per ASTM D 2247-87
- c. QUV test as achieved by ASTM D4587 no visible loss of film integrity and no chalking greater than #8 after 500 HR, as measured by ASTM D 4214-89

C. ACM's (.019") Rainware Products are available in a wide variety of colors to match our Edge Metal Products as well as most major manufacturers'. Please refer to our color literature for color availability.

ACM's (.024") Rainware Products are only available in three colors (White, Royal Brown, Black)

APPLICATIONS

ACM Aluminum Rainware products are designed for residential and light commercial applications. All accessories shall be attached per the contractor's direction.

CONSIDERATIONS

Corrosion is likely to happen with direct contact of aluminum product(s) to certain dissimilar materials or water run-off from same such materials. Care should be taken to avoid contact of aluminum with any corrosive materials during the installation process, including, but not limited to: concrete, stucco, pretreated lumber, corrosive chemicals, fiber cement products, masonry cement, roofing made with metallic granules of dissimilar metals (copper, zinc, steel, etc.), salt, and dissimilar metals.

- The standard thickness tolerance for products made from aluminum sheet material shall be -0.002".

ACM – Beloit
1600 Park Avenue
Beloit, WI 53511
ph :608.365.0296
fax: 608.365.0493

ACM – Houston
11615 Brittmoores Park Dr
Houston, TX 77041
ph: 713.466.1797
fax: 713.466.5404

ACM –Apollo Beach
6938 N Hwy. 41
Apollo Beach, FL 33572
ph: 813.671.3444
fax:813.671.5650

ACM - Lodi
1307 E Pine St.
Lodi, CA 95240
ph: 209.334.1489
fax: 209.334.4589